

P1 1112681

RECEIVED

15 JAN 2004

WIPO

PCT

THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE
United States Patent and Trademark Office

January 12, 2004

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE.

APPLICATION NUMBER: 60/422,571

FILING DATE: *October 31, 2002*

RELATED PCT APPLICATION NUMBER: *PCT/US03/34318*

By Authority of the
COMMISSIONER OF PATENTS AND TRADEMARKS



N. Woodson
N. WOODSON
Certifying Officer

PRIORITY DOCUMENT
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH
RULE 17.1(a) OR (b)

BEST AVAILABLE COPY

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a currently valid OMB control number.

hereby certify that this paper is being deposited in the United States Postal Service as Express mail in accordance with the provisions of 39 U.S.C. 1103 and 1106. Signature: L. Juettner Express Mail No. 846173123 45 Date: 10-31-2002

PROVISIONAL APPLICATION FOR PATENT

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

Express Mail Label No.

EL 846173123 US

INVENTOR(S)

Given Name (first and middle [if any])	Family Name or Surname	Residence (City and either State or Foreign Country)
Gopal	Iyengar	Wisconsin Rapids. WI

☒ Additional inventors are being named on the 1 separately numbered sheets attached hereto

TITLE OF THE INVENTION (500 characters max)

HIGH STRENGTH DIMENSIONALLY STABLE CORE

Direct all correspondence to:

CORRESPONDENCE ADDRESS



Customer Number

24978

OR

Type Customer Number here

Place Customer Number
Bar Code Label here



Firm or
Individual Name

Paul G. Juettner

Address

Greer, Burns & Crain, Ltd.

Address

300 S. Wacker Drive, Suite 2500

City

Chicago

State

IL

ZIP

60606

Country

US

Telephone

312-360-0080

Fax

312-360-9315

ENCLOSED APPLICATION PARTS (check all that apply)



Specification Number of Pages

8



CD(s), Number



Drawing(s) Number of Sheets

10



Other (specify)

Assignment;
Power of Attorney



Application Data Sheet. See 37 CFR 1.76

METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT



Applicant claims small entity status. See 37 CFR 1.27.



A check or money order is enclosed to cover the filing fees



The Commissioner is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number:

07-2069



Payment by credit card. Form PTO-2038 is attached.

FILING FEE
AMOUNT (\$)

\$160.00

The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.



No.



Yes, the name of the U.S. Government agency and the Government contract number are:

Respectfully submitted,

SIGNATURE

TYPED or PRINTED NAME

Paul G. Juettner

TELEPHONE

312-360-0080

Date

10/31/2002

REGISTRATION NO.
(if appropriate)
Docket Number:

30,270

0329.66419

USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT

This collection of information is required by 37 CFR 1.51. The information is used by the public to file (and by the PTO to process) a provisional application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the complete provisional application to the PTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, Washington, D.C. 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Box Provisional Application, Assistant Commissioner for Patents, Washington, D.C. 20231.

[The page contains faint, illegible markings or bleed-through from the reverse side.]

Approved for use through 10/31/2002. OMB 0651-0032
U.S. DEPARTMENT OF COMMERCE

U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

0329.66419

INVENTOR(S)/APPLICANT(S)		
Given Name (first and middle [if any])	Family or Surname	Residence (City and either State or Foreign Country)
Jeffrey G.	Dicks	Nekoosa, WI
Mark D.	Ellis	Wisconsin Rapids, WI
Gary G.	Glodoski	Stevens Point, WI

Number 2 of 2

WARNING: Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.

HIGH STRENGTH DIMENSIONALLY STABLE CORE

Field of the Invention

This invention relates to paperboard cores and tubes, and to paperboard for making cores and tubes.

Background of the Invention

In the manufacture of paper, paper is wound onto cores. Cores are conventionally manufactured from laminated, spirally wound paperboard. It is important that cores have sufficient crush strength. Dimensional stability of cores is also important in roll handling operations.

Moisture content in paper varies considerably from grade to grade depending on the manufacturing process. Similarly, paperboard cores are made at different moisture levels, depending on the absorption characteristics of the paperboard from which it is made and the adhesive used to glue the board layers to form a laminated core. As a result, in the winding of paper onto cores, there is typically a moisture content difference between the paper and the core. A difference in moisture content between the paper and core causes moisture to migrate. Moisture migration from the core to the paper and vice versa can cause corrugations and wrinkling in the paper, and in some cases core bursts, resulting in paper losses.

Papermills today make wide paper rolls by winding different webs of paper onto a single core. Often, the different webs have different moisture contents, aggravating moisture migration problems. Further, these wide rolls require high strength cores to support the substantial weight of the paper.

Summary of the Invention

It is an object of the invention to provide a high strength, dimensional stable core, with improved resistance to moisture migration. It is a further object of the invention to provide a high strength, water resistant paperboard that has utility in the fabrication of such cores.

The core of the invention is manufactured from spirally wound paperboard having improved water resistance. The paperboard is made from furnish comprising a mixture of 25-70% doubleliner kraft ("DLK"), and 25-70% recycled corrugated containers ("OCC"), and 30-50% recycled cores and/or other cores waste ("corebale"). The furnish should have a freeness of 150-275 CSF. The furnish is modified by adding 1-60 lbs/ton alum, and 3-40 lbs/ton of liquid size. Preferably, 0.2 - 1. lbs/ton microparticle silica, and 16-50 lbs/ton modified cationic starch, and/or 2-8 lbs/ton of a dry strength agent may also be added, but are not required.

It has been discovered that the combination of alum and a liquid size substantially improves water resistance. A suitable alum product is aluminum

sulfate solution available from General Alum & Chemical Corporation, Holland, Ohio.

A preferred liquid size is Ultra-pHase® cationic dispersed size manufactured by Hercules Incorporated, Wilmington, Delaware.

The microparticle silica is added to improve the drainage in the paperboard making process. A preferred microparticle silica is Nalco 8692 Papermaking Aid, an aqueous dispersion of an inorganic hydrous oxide microparticle, manufactured by Nalco Chemical Company, Naperville, Illinois.

Other microparticle silica products may be used as well.

The modified cationic starch improves strength. A preferred starch product is Penford Topcat 776 cationic additive, manufactured by Penford Products Co., Cedar Rapids, Iowa. Other suitable starch products are Avebée Amylofax 3300C and Amylofax-HS.

The dry strength agent improves strength and contributes somewhat to improvement in water resistance. Suitable dry strength agent is Callaway 911 dry strength agent, manufactured by Vulcan Performance Chemicals, Birmingham, Alabama.

The forgoing optional additives are selected and added to as required to produce the required properties of the core. For example, if a high strength is not required, one could use little or no starch or dry strength agents. Other additives could be used, for example a wet strength agent.

The modified furnish is manufactured into paperboard by known manufacturing techniques, such as fourdrinier or multiple cylinder papermachine, to produce a finished paperboard having a basis weight of 40-142 lbs per 1000 sq/ft., a caliper of about 0.013 to .041 inches, a density of 0.7 to 1.0 g/cm³ and a moisture content of between about 3-6 percent. The moisture content of the cores preferably should be as close as possible to the moisture content of the paper to be wound onto the cores.

The paperboard is then wound with conventional core machinery to form paperboard cores having between 3-32 plies. For example, one embodiment of the invention comprises high strength cores for paper rolls, which have 20-32 plies. Another application of the invention is for cores for adhesive tape and other small tube applications, which have 3-7 plies. In smaller cores made in accordance with this disclosure have a lower core crush variability due to humidity and improved dimensional stability. The preferred adhesive used in winding the cores is polymer base, such as latex; however, other adhesives may be used.

Testing on the cores made in accordance with the foregoing exhibited increased crush strength, and increased water holdout. The cores exhibited reduced moisture carry over, and low core length shrinkage. Other benefits include reduced core warpage and less variability in core inner and outer diameter.

Detailed Description of Preferred Embodiments

Examples of the improved high strength, dimensional stable cores of the invention are provided as follows:

GP1 Standard

The furnish comprised: 95 lbs DLK, 1,000 lbs OCC and 1,400 lbs corebale. Paperboard was manufactured from the furnish on a conventional board machine. The resulting paperboard had a caliper of about 0.02 inches and a basis weight of about 80 lbs/1,000 square feet. The core was wound in conventional process, having a lead-in ply and 30 structural plies formed with the above furnish.

The cores had an internal diameter of 3.025 inches and a wall thickness of 0.66 inches.

Paperboard and cores were tested for water absorption and strength. The paperboard had a water absorption of less than about 950 - 1150 cgs based on the amount of water absorbed by a 6" x 6" paper board sample submerged in a water bath for 10 minutes. The paperboard had a ZDT bond strength of 100 "Z"directional internal bond strength of board tested on a ZDT tester. Core crush strength was 800-850 lbs on a 4" length of core, and Dynamic load strength of 26-29 lbs/4" section. The moisture content of the core was 9-11%.

Example P1

The same paperboard and cores as in Example GP1 were manufactured, except that the following constituents were added to the furnish:

Callaway 911 dry strength agent @ 6 lbs/ton dry weight

Ultra-Phase liquid size @ 31 lbs/ton dry weight

Alum was varied between 30 and 60 lbs/ton dry weight

Paperboard and cores were tested for water absorption and strength.

The paperboard had a water absorption of less than 400 cgs based on the amount of water absorbed by a 6" x 6" paper board sample submerged in a water bath for 10 minutes. The paperboard had a ZDT bond strength 105 - "Z" directional internal bond strength of board tested on a ZDT tester. Core crush strength was 1135 lbs on a 4" length of core, and Dynamic load strength of 35.2 lbs/4" section. The moisture content of the core was 7.86%.

Example P2

The same paperboard and cores as in Example GP1 were manufactured, except that the following constituents were added to the furnish:

Callaway 911 dry strength agent @ 6 lbs/ton dry weight

Ultra-Phase size @ 16 lbs/ton dry weight

Avebe Amylofax-HS starch was varied between 33 and 50 lbs/ton dry weight

Alum was varied between 30 and 60 lbs/ton dry weight

Paperboard and cores were tested for water absorption and strength. The paperboard had a water absorption of less than 400 cgs based on the amount of water absorbed by a 6" x 6" paper board sample submerged in a water bath for 10 minutes. The paperboard had a ZDT bond strength 112-150 - "Z"directional internal bond strength of board tested on a ZDT tester. Core crush strength was 1238 lbs on a 4" length of core, and Dynamic load strength of 36.3 lbs/4" section. The moisture content of the core was 8.43%.

Example P5

The same paperboard and cores as in Example GP1 were manufactured, except that the following constituents were added to the furnish:

Penford Topcat 776 cationic starch @ 30 lbs/ton dry weight

Ultra-pHase size @ 3 lbs/ton dry weight

Alum @ 4 lbs/ton dry weight.


Paperboard and cores was tested for water absorption and strength. The paperboard had a water absorption of less than 700 cgs based on the amount of water absorbed by a 6" x 6" paper board sample submerged in a water bath for 10 minutes. The paperboard had a ZDT bond strength 125-141 - "Z"directional

internal bond strength of board tested on a ZDT tester. Core crush strength was 1299 lbs on a 4" length of core, and Dynamic load strength of 36.5 lbs/4" section. The moisture content of the core was 7.23%.

Attached as Figures 1-10 are graphs that summarize comparative testing on the cores of the foregoing examples.



Figure-1: Custom Made Cores
Effect of Ambient Drying On Core Moisture





STORAENSO

**Figure-2: Custom Made Cores
Effect of Ambient Drying On Core Crush**






Figure-3: Custom Made Cores
Effect of Ambient Drying On Torsional Strength



**Figure-4: Custom Made Cores
Effect of Ambient Drying On Length Shrinkage**



**Figure-5: Custom Made Cores
Effect of Ambient Drying On Core Warp**





Figure-6: Custom Made Cores
Effect of Ambient Drying On Core Outer Diameter



—○— P1
—□— P2
—△— P5
—×— GP1 Std



STORAENSO

**Figure-7: Custom Made Cores
Effect of Ambient Drying On Core Inner Diameter**






Figure-8: Custom Cores
Effect of Oven Drying @120 Deg F For 16 Hours on Core Moisture








Figure-9: Custom Cores
Effect of Oven Drying @ 120 deg F for 16 hours on Core Crush



**Figure-10: Moisture Migration Study Winding 1.5%
Moisture Paper on Ambient Dried Cores-B:Research**



Practitioner's Docket No. 0329.66419**PATENT****IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**In re application of: Gopal Iyengar, Jeffrey G. Dicks, Mark D. Ellis and Gary G. Glodos☐ Application No.: /☒ Filed herewithFor: HIGH STRENGTH DIMENSIONALLY STABLE CORE**POWER OF ATTORNEY FOR PROVISIONAL APPLICATION**

Each inventor, identified above and signing below, hereby appoints the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith:

(list name(s) and registration number(s))

Paul G. Juettner	Registration No.	30,270
Thomas R. Juettner	Registration No.	16,158
Carole A. Mickelson	Registration No.	30,778
Thomas R. Fitzsimons	Registration No.	40,607

Correspondence address: GREER, BURNS & CRAIN, LTD.300 S. Wacker Drive, Suite 2500 Chicago, IL 60606Direct telephone calls to: Paul G. Juettner

Tel. No.: (312) 360-0080

(check the following item, if applicable)

- ☒ Each inventor, identified above and signing below, authorizes the above named attorney(s) and/or agents to accept and follow instructions from his/her representative(s).

	Inventor(s)	Signature
Date: 6/16/02	<u>Gopal G. Iyengar</u>	<u>Gopal</u>
Date: 7-17-02	<u>Henry H. Albrecht</u>	<u>Henry H. Albrecht</u>
Date: 7/18/02	<u>MARK D. ELLIS</u>	<u>Mark D. Ellis</u>
Date: 7/18/02	<u>Jeffrey G. Dicks</u>	<u>Jeffrey G. Dicks</u>

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☒ BLACK BORDERS

☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES

☐ FADED TEXT OR DRAWING

☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING

☐ SKEWED/SLANTED IMAGES

☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS

☐ GRAY SCALE DOCUMENTS

☒ LINES OR MARKS ON ORIGINAL DOCUMENT

☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.